



BioLogiQ creates plastics from polysaccharides found in plants. These plastics are designed to enhance both the functional and environmental performance of the packages and products produced with them.

All BioLogiQ compounded plastics start with **NuPlastiQ** BioPolymer, a 100% natural, renewably sourced, plant-based biopolymer.

## Description

- One of the BioBlend® XP family of high performance BioPolymers designed for blown film applications.
- BioBlend® XP 22150 is a masterbatch that contains 50% NuPlastiQ GP BioPolymer compounded with HDPE.
- Made from 50% annually renewable agricultural resources.
- Supplied in pellet form.

## Applications

- Used for film applications requiring strength and stiffness like T-shirt bags, trash can liners, industrial liners and heavy duty bags.

## Properties

PHYSICAL	TEST METHOD	NOMINAL VALUE	UNITS
Density:	ASTM D792	1.17	g/cm <sup>3</sup>
<b>THERMAL</b>			
Melt Flow Index	ASTM D1238	0.3	g/10 min (190 °C/10 kg)
Melting Temperature Range:	ASTM D3418	131	° C
<b>ADDITIONAL INFORMATION</b>			
Moisture Content: <sup>(1)</sup>	ASTM D6980	≤ 0.5	%

Table Notes:

- 1) Moisture content was measured with an infrared moisture analyzer at 105°C for 10 minutes.
- 2) These values are typical properties only and should not be used for specification purposes. End users should confirm results with their own tests.

## Processing Considerations

- XP 22150 is designed to be diluted with polyethylene to a final NuPlastiQ® content between 10% and 35%.
- XP 22150 can be run on existing process equipment with a few adjustments.
- Films made with NuPlastiQ are more sensitive to processing conditions such as temperature profile, residence time, die gap, and blow-up ratio. See the NuPlastiQ Film Processing Guide for additional information.
  - A typical recommended temperature profile will be in the 160°C – 190°C range.
  - Depending on equipment, process conditions, and residence time, as temperatures increase in this range the glycerin plasticizer may experience some volatilization. This may cause a slight odor and/or smoke and is expected under normal processing conditions. Always use proper ventilation. See the BioBlend® XP 22150 SDS for details.
- Some equipment (multi-layer, higher output, lower residence time) may allow for higher processing temperatures (190°C - 200°C).
- Melt temperatures above 205°C may cause material degradation, lensing and fish-eyes in the film.

Product: **BioBlend® XP 22150**



- When extruder operation has to be stopped temporarily, it is recommended to purge the material in the barrel before resuming film processing.
- This TDS covers the following BioBlend® XP BioPolymers: XP 22150 and XP 22151

## Storage and Drying

- BioLogiQ BioBlends are dried after production and shipped in sealed moisture-proof bags that are ready to use as supplied. They should be stored indoors in the sealed container away from heat until used.
- If pellets are exposed to a humid environment, they will absorb moisture from the air. If needed, dry pellets by introducing warm dry air at no more than 80°C for 1-4 hours.
- The estimated moisture content of a BioLogiQ BioBlend can be measured with an infrared moisture analyzer at 105°C for 10 minutes. The result of the measurement will not perfectly equal the moisture content, due to possible partial evaporation of plasticizer. The result from this test should be <0.5% moisture prior to processing.