


Samples to test at OWS for ASTM 5338 Aerobic Biodegradation Testing

Item #	Product	ESR Content	PE	Other	Thickness A (mils)	Biodegradation @ 13 d	Biodegradation @ 26 d	Biodegradation @ 45d
MBR16070601	ESR/PBAT Film - Mulch or Bag Film	40%	49%	11%	1.50	42.5%	62.4%	95.3%



MBR16070601 A bag made with 40% ESR, 49% PBAT and 11% Fossil-fuel Compatibilizer degraded 75% (95% relative) in 45 days in an industrial compost environment

